

PRODUCT INFORMATION



RESOPAL

PRODUCTS AND PRODUCT DATA – ORIGINAL RESOPAL® >2018 – HPL EN 438

| | Plain Colours | Woodgrains | Stones | Materials | Special decors | Sizes [mm] | Thickness [mm] |
|---|---------------|------------|--------|-----------------------------------|-----------------------------|--|----------------|
| RESOPAL® Decors | 120 | 54 | 9 | 30 | | 3050 x 1320 | 0.8 |
| | | | | | | 2600/3050/3650 x 1320 | 0.6-1.2 |
| | | | | | | 2180 x 915/1020/1320 2600 x 1320 | |
| | | | | | | 5200 x 1320 | 0.6-1.0 |
| Wooden Spirit | | 9 | | | | 3050 x 1320 | 0.8 |
| Ceramics | | | 3 | 6 | | 3650/5200 x 1320 | 0.8 |
| High Gloss | | 3 | 4 | 2 | | 3050 x 1320 | 0.8 |
| Metal on RESOPAL® Real metal | | | | | 10 Metals | 2440 x 1220 | 0.8 |
| | | | | | 3908-LN/3908-SN | 3050 x 1320 | |
| | | | | | 3900-GB/3903-AN/ 3908-GN | 3050/3650 x 1320 | |
| Doors Door collection | 50 | 54 | | | | 2180 x 915/1020/1320 2350 x 1320 2600** x 1380 | 0.8 |
| RESOPAL® Components | 120 | 54 | 9 | 30 | | 3050/3650 x 1320 2180 x 915/1020/1320 | 8-40 |
| RESOPAL® Massiv Self supporting solid board from 2mm up to 42mm | 120 | 54 | 9 | 30 | | 3050 x 1320 | up to 25 |
| | | | | | | 3650 x 1320 2180 x 1320 2180 x 915/1020 | up to 42 |
| Color in RESOPAL® Coloured laminated solid board | 120 | 54 | 9 | 30 | | 3650 x 1320 | 6/8/10/12 |
| RESOPAL® Pure White With a white core | | | | | 0105/9417 | 3050/3650 x 1320 | 0.8-1.2 |
| | | | | | | 3050/3650 x 1320 | 1.0 |
| | | | | | | 3050/3650 x 1320 | up to 12 |
| ORIGINAL RESOPAL® Worktops | | | | | | 3650 x 600/900 | 38 |
| | | | | | | 3650/5200 x 600 | |
| | | | | | | 3650/5200 x 900 | |
| | | | | | | 3650/5200 x 1200 | |
| | | | | | | 3650/5200 x 640 | |
| RESOPAL® WAP Upstands of identical material with the same decor for worktops with ORIGINAL RESOPAL® | | | | | | 3650 length | |
| RESOPAL® Edges ORIGINAL RESOPAL® edge strips | | | | | | 3650 x 44 | 0.8 |
| RESOPLEX® Straight Ahead | | | | | | 3650 x 600/900/1200 5200 x 600/900/1200 3650/5200 x 1310 | 38.1 |
| RESOPLAN® | | | | | | 3050 x 1320 3650 x 1320 2180 x 1020 | 6/8/10/12 |
| RESOPAL® X-Line | | | | | | 3050/3650 x 1320 2180 x 1020 | 6/8/10/12 |
| Motiv/Digital in RESOPAL® | | | | | | 3050 x 1320 [Print: 3000 x 1300] | 1.0 |
| vectogramm® in RESOPAL® | | | | | | max. 5000 x 1900 | |
| RESOPAL ² Homogeneous material mix without seems and joints | | | | | | 3050 x 1320 2180 x 1020/1320 | 0.8 |
| RESOPAL®+HIPERCARE® Anti-bacterial surface | | | | All colours and printed decors | | 3050/3650 x 1320 2180 x 915/1020/1320 | 0.8 |
| RESOPAL® Direct The self-adhesive RESOPAL® | | | | All colours and printed decors | | 3050/3650 x 1320 2180 x 1020/1320 | 0.8 |
| RESOPAL® Magnetic | | | | | | 3050 x 1220 3050 x 1220 | 1.2 4-6 |
| RESOPALIT® PEFC certified | 11 | 12 | | | | 3300 x 2070 | 10/19 |
| | 8 | | | 10 | | 3050 x 1250 | |
| RESOFLOOR® | | | | | | 1488 x 293 | 11.4 |
| RESOPAL SpaStyling® Titanium Floor | | | | | | 985 x 400 | 7.8 |
| RESOPAL SpaStyling® Board | | | | | | 3050 x 1320 | 7.8 |

| | Special decors | Sizes [mm] | Thickness [mm] |
|-------------|----------------|-------------|----------------|
| RE-Y-STONE® | | 3050 x 1320 | 0.8-1.5 |

| | Special decors | Sizes [mm] | Thickness [mm] |
|---------------------------------|----------------|---------------------------|----------------|
| WILSONART® Solid Surface SSV | 15 | 3660 x 760 3660 x 1370 | 3 |
| Gibraltar | 15 | 3660 x 760 | 12.5 |
| Gibraltar Glass | 3 | 3050 x 915 | 12.5 |
| Worktops, sinks, basins, etc. | | on request | |

* more surfaces on request ** Cut to size

PRODUCT INFORMATION

| Finish | Quality | From stock >2018 | Made to order | Notes | Page |
|--|--|--------------------------------------|--|--|-----------------|
| depends on decor all surfaces | Postforming Postforming Standard Postforming | X | min. 30 sheets then in multiples of 4 or 6 sheets with 50% upcharge on request | | 18 - 119 |
| WS | Postforming | X | | further decors / sizes on request | 68 - 73 |
| KS | Postforming | X | | further decors / sizes on request | 110 - 115 |
| HW | Postforming | X | | further decors / sizes for HW / TH on request | 116 - 119 |
| depends on decor | Standard Postforming Postforming | X X X | min. 10 pcs | | 120 - 123 |
| 60 / * | Standard Standard | X | min. 12 pcs / also in B1 available (FR Grade) | further decors on request | 124 - 127 |
| depends on decor | | | min. 20 pcs | special sizes / special elements on request | 158 - 162 |
| 60 / Woodgrains also in EM / WH / FW | Standard | | min. 3 per decor / size / thickness / finish also in B1 available (FR Grade) | 2 mm / 3 mm have the option of one side sanded or unsanded | 179 - 181 |
| 60 | Standard | | min. 3 per decor / size / thickness | core only black (1.2 mm) / white (0.8 mm) | 181 |
| 20 / 60 / EM HW 20 / 60 / EM | | | min. 30 pcs or min. 6 pcs with 50% upcharge / on request | further decors on request | 143 |
| depends on decor | D-Profile D-Profile U-Profile milled edge D- and U-Profile | X | single side postformed min. 16 pcs single side postformed min. 8 pcs single side postformed min. 8 pcs both side postformed min. 48 pcs | special edition up to 96 worktops per type; same profile / width / thickness | 165 |
| | | 10 per decor | | 3 different lip colours | |
| | | 10 per decor | | further decors on request | |
| depends on decor | D-Profile | | | 1.5 mm PP edge, 2.0 mm ABS edge or 1.5 mm 3D edge depending on the decor | 167 |
| 60 | Standard | | min. 3 per decor / size / thickness / also in B1 available (FR Grade) | other thicknesses on request | 184 - 188 |
| 60 | Standard | | min. 3 per decor / size / thickness / also in B1 available (FR Grade) | other thicknesses on request | 189 |
| 60 / * | | | depending on enquiry | further sizes on request | 149 - 157 |
| | | | depending on enquiry | | 181 |
| 60 / * | Standard | | specification, price and delivery time on request | | 145 |
| depends on decor | Postforming / Standard | 0105 / 0160 / 9417 / D 92 / D 403 | min. 16 sheets for printed decors, for Plain Colours on request | | 146 - 147 |
| depends on decor | Standard | | min. 4 pcs per specification (special made to order on request) | | 144 |
| 20 / 60 / EM | | | | sanded on the back side magnetic on both sides | 145 |
| 60 | | X X | further sizes and thicknesses on request | further decors on request | 128 - 129 / 162 |
| TH | | X | | | 169 - 171 |
| depends on decor | | X | | | 172 - 177 |
| depends on decor | | X | | further decors on request | 172 - 177 |

| Finish | Quality | From stock >2018 | Made to order | Notes | Page |
|------------------|---------|------------------|---------------|-------|-----------|
| depends on decor | | X | | | 192 - 195 |

| Finish | Quality | From stock >2018 | Made to order | Notes | Page |
|--------|---------|------------------------|-----------------------------|-------|-----------|
| | | D 354 / 1573 / D 92-SL | min. 160 pcs min. 90 pcs | | 197 - 198 |
| | | D 354 / 1573 / D 92-SL | min. 30 pcs | | 197 - 198 |
| | | | | | 197 - 198 |

RESOPAL® – Technical data and requirements acc. to EN 438

| | Test method acc. to EN 438, Part 2 | Unit | Specification, Type of material | | | | | | | |
|---|--|---------------------|---------------------------------|-----------|-------------|-----------|-----------|--------------|--------------|----------|
| | | | RESOPAL® 0.6 - 1.2 mm | | | RESOPAL® | | RESOPLAN® B2 | RESOPLAN® B1 | RESOPAL® |
| | | | Standard | F-Quality | Postforming | Massiv B2 | Massiv B1 | | | Worktops |
| Abrasion resistance | 10 | [index number] | 3 | 3 | 3 | 3 | 3 | | | 3 |
| Impact resistance ¹⁾ | 20 | [index number] | 4/3 | 4/3 | 4/3 | 4 | 4 | | | 3 |
| Scratch resistance ²⁾ | 25 | [rating] | 4/3/2 | 4/3/2 | 4/3/2 | 4/3/2 | 4/3/2 | | | 3/2 |
| Resistance to dry heat ²⁾ | 16 | [rating] | 3-5 | 3-5 | 3-5 | 3-5 | 3-5 | | | 3-5 |
| Resistance to cigarette burning | 30 | [rating] | ≥ 3 | ≥ 3 | ≥ 3 | ≥ 3 | ≥ 3 | | | ≥ 3 |
| | ISO 4586 method 18 B | [sec] | ≥ 120 | ≥ 100 | ≥ 100 | | | | | |
| Light fastness | 27 | [grey scale rating] | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 | 4.5-5 | 4.5-5 | 4-5 |
| Dimensional stability at elevated temperature | 17 | | | | | | | | | |
| | | longitudinal | [%] | 0.4-0.6 | 0.4-0.6 | 0.4-0.6 | 0.15 | 0.15 | 0.15 | 0.15 |
| transverse | [%] | 0.8-1.0 | 0.8-1.0 | 0.8-1.0 | 0.30 | 0.30 | 0.30 | 0.30 | | |
| Resistance to immersion in boiling water: | | | | | | | | | | |
| Appearance ²⁾ | 12 | [rating] | 3-5 | 3-5 | 3-5 | 3-5 | 3-5 | | | |
| Resistance to damp heat (100 °C) | EN 12721 | [rating] | 3-5 | 3-5 | 3-5 | 3-5 | 3-5 | | | |
| Increase in weight | | [%] | | | | < 2 | < 3 | | | |
| Increase in thickness | | [%] | | | | < 2 | < 3 | | | |
| Resistance to water vapour | 14 | [rating] | ≥ 4 | ≥ 3 | ≥ 3 | ≥ 4 | ≥ 4 | | | |
| Formability | 31 | | | | | | | | | |
| HPL 0.8 mm | | [mm] | | | approx. 7 | | | | | |
| HPL 0.6 mm | | [mm] | | | approx. 5 | | | | | |

¹⁾ depending on thickness ²⁾ depending on texture
Highly abrasion-resistant version on request.

Other test methods: ISO 4586, part 2

Other technical data

| | Test method | Unit | Specification, Type of material | | |
|--|-------------------------------|--------------------------|---|------------------------------------|------------------------|
| | | | RESOPAL® 0.6 - 0.8 mm | RESOPAL® Massiv | RESOPLAN® B2 |
| Density | EN ISO 1183 | [g/cm ³] | 1.4 | 1.4 | 1.4 |
| Tensile strength longitudinal transverse | EN ISO 527-2 | [MPa] | | 100 70 | 100 70 |
| Flexural strength longitudinal transverse | EN ISO 178 | [MPa] | | 140 100 | 140 100 |
| Modulus of elasticity longitudinal | EN ISO 178 | [MPa] | | 14000 | 14000 |
| | | [MPa] | | 10000 | 10000 |
| Co-efficient of thermal expansion longitudinal | DIN 51045 +80 °C / -20 °C | [1/K] | 0.9 x 10 ⁻⁵ | 0.9 x 10 ⁻⁵ | 0.9 x 10 ⁻⁵ |
| | | [1/K] | 1.6 x 10 ⁻⁵ | 1.6 x 10 ⁻⁵ | 1.6 x 10 ⁻⁵ |
| Thermal conductivity | DIN 52612 | [W/(m x K)] | approx. 0.3 | approx. 0.3 | approx. 0.3 |
| Calorific value | ISO 1716 | [MJ/kg] | approx. 20 | approx. 20 | approx. 20 |
| Water steam permeability | DIN 53122 | [g/(m ² x d)] | approx. 2-4 | | |
| Surface resistance (antistatic behaviour) | EN 61340-2-3 (no static load) | [Ohm] | 10 ⁹ - 10 ¹¹ | 10 ⁹ - 10 ¹¹ | |
| | | | Worktops – RESOPAL® High Pressure Laminates (HPL) acc. to EN 438 / 0.6-0.8 mm particle board, E1 | | |
| Emission Formaldehyde | | [ppm] | ≤ 0.1 | | |
| Bonding | DIN EN 204 | | D3 | | |
| Edge radius ¹⁾ | | [mm] | 3.0 | | |

¹⁾ with almost all decors

PRODUCT INFORMATION

RE-Y-STONE® Bio Composite Panel – Technical data

| | Test method | Unit | RE-Y-STONE® Bio Composite Panel | |
|---|-----------------|---------------------------------------|------------------------------------|------------------------------------|
| | | | Thickness: 0.8-3.0 mm | Thickness: > 3.0 mm |
| Density | ISO 1183 | [g/cm ³] | ca. 1.4 | ca. 1.4 |
| Impact resistance | on the basis of | | | |
| a) with a ball with small diameter | ISO 24335 | [N] | ≥ 20 | ≥ 25 |
| b) with a ball with large diameter | | [mm] | ≥ 1000 | ≥ 1500 |
| Scratch resistance ^{1) 2)} | EN 15186 | [N] | 1.0-2.5 | 1.0-2.5 |
| Resistance to fading (Xenon arc lamp) | EN 15187 | [grey scale rating] (EN 20105-A02) | 3-4 | 3-4 |
| Water absorption (24 h/20 °C) | EN ISO 62 | [%] | ≤ 15 | ≤ 8 |
| Thickness increase (24 h/20 °C) | EN 317 | [%] | ≤ 18 | ≤ 10 |
| Resistance ¹⁾ against dry heat (140 °C) | EN 12722 | [rating] | ≥ 3 | ≥ 3 |
| Resistance ¹⁾ against wet heat (100 °C) | EN 12721 | [rating] | ≥ 3 | ≥ 3 |
| Resistance to cigarette burning | DIN 68861-6 | Class of use | 6C | 6C |
| Dimensional stability in relation to relative humidity | EN 318 | | | |
| longitudinal | | [%] | approx. 0.1 | approx. 0.1 |
| transverse | | [%] | approx. 0.2 | approx. 0.2 |
| Water steam permeability | DIN 53122 | [g/(m ² x d)] | approx. 1-3 | not defined |
| Surface resistance (antistatic behaviour) | EN 61340-2-3 | [Ohm] | 10 ⁹ - 10 ¹² | 10 ⁹ - 10 ¹² |
| Flexural strength | EN ISO 178 | | | |
| longitudinal | | [N/mm ²] | not defined | approx. 100 |
| transverse | | [N/mm ²] | not defined | approx. 70 |
| Modulus of elasticity | | | | |
| longitudinal | | [N/mm ²] | not defined | approx. 10000 |
| transverse | | [N/mm ²] | not defined | approx. 7000 |
| Fire behaviour | DIN 4102-1 | - | B2 | B2 |

¹⁾ depending on texture ²⁾ depending on colour

RESOPAL® Flooring – Technical data

| Technical Details | | RESOFLOOR® | RESOPAL SpaStyling® Titanium Floor |
|----------------------|--|--------------------|------------------------------------|
| Dimension | | ~ 1488 mm x 293 mm | on request |
| Thickness of element | | ~ 11.4 mm | ~ 7.8 mm |
| Weight | | - | 4.9 kg/m ² |

| Design | | | |
|---|--|---|---|
| Surface layer | | RESOPAL® HPL High Wear 1.0 mm | RESOPAL® HPL |
| Substrate | | HDF 9.4 mm (moisture-proof) | glass fibre reinforced composite core |
| Backing | | RESOPAL® HPL 1.0 mm | RESOPAL® HPL |
| Click system (glueless installation) | | Produced under Licence from the UNILIN Group | Produced under Licence from Välinge (2G) |

| Substrate | Test method | Unit | | |
|-----------------------------|-----------------|------|---|-----|
| Swelling in thickness (q24) | EN 317 | | - | 0 % |
| Swelling after boiling test | EN 1087-1 (MOD) | | - | 0 % |

| Characteristics | Test method | Unit | | |
|--|---------------------------|------------------------|--|--|
| Class of use 23 ¹⁾ | EN 685 | | Corridors, living rooms, kitchen, home offices | - |
| Class of use 32 ²⁾ | EN 649, Tab. 3 | | - | Small offices, hotels, boutiques |
| Class of use 33 ³⁾ | EN 685 | | Large offices, public buildings, department stores | - |
| Click system | - | | Patented click system | Patented click system |
| Surface | - EN 438 | | Shock/impact resistant | Shock/impact resistant |
| Abrasion resistance | EN 13329 | | AC 5 ≥ 6000 revolutions | min. AC 5 ≥ 6000 revolutions |
| Impact resistance | EN 13329 | | IC 3 | IC 2 |
| Scuff/mar resistance | EN 16094 Martindale | | High scuff/mar resistance | - |
| Fire behaviour | EN 13501-1 DIN 4102-14 | | B _{fl} -s1 B1 | C _{fl} -s1 - |
| Slip resistance | DIN 13893 EN 14041 | | ≥ 0.3 Class: DS | ≥ 0.3 Class: DS |
| Anti-slip property | BGR 181 DIN 51130 | | - | R 9 |
| Resistance on staining | EN 438-2 | [rating] | Group 1+2: ≥ 5 Group 3: ≥ 4 | Group 1+2: ≥ 5 Group 3: ≥ 4 |
| Resistance to cigarette burning | EN 438-2 | [rating] | ≥ 4 durable (no damage of the surface) | ≥ 4 durable (no damage of the surface) |
| Light fastness (xenon arc) | EN 438-2 | [grey scale rating] | ≥ 4 | ≥ 4 |
| Surface resistance (antistatic behaviour) | DIN 61340-2-3 | [Ohm] | 10 ⁹ - 10 ¹² (no static charge) | 10 ⁹ - 10 ¹² (no static charge) |
| Thermal insulation | EN 12664 | [m ² x K/W] | < 0.09 (float installation) | < 0.12 (float installation) |
| Formaldehyde emission | EN 717-2 | | E1 | E1 |

¹⁾ heavy domestic use

²⁾ normal commercial use

³⁾ heavy commercial use

WILSONART® Solid Surface – Technical data

| | Test method | Unit | Wilsonart® SSV | Gibraltar | Gibraltar Glass |
|--|---------------------------------------|-------------------------------|------------------------|------------------------|------------------|
| Density | ISO 1183 | [g/cm ³] | 1.59 | 1.60 | 1.30 |
| Flexural strength | EN ISO 178 | [N/mm ²] | 50 | 50 | 28 |
| Modulus of elasticity | EN ISO 178 | [N/mm ²] | 5000 | 6000 | 5000 |
| Co-efficient of thermal extension | DIN 51045 +80°C / -20°C | [1/K] | 3.4 x 10 ⁻⁵ | 3.4 x 10 ⁻⁵ | - |
| Thermal conductivity | DIN 52612 | [W/(m x K)] | | | - |
| Impact strength | EN 438-2 | [cm] | | ≤ 250 | < 150 |
| Abrasion resistance | DIN 68861-2 ¹⁾ EN 438-2 | stress class [revolutions] | 2A >> 1000 | 2A >> 1000 | 2A >> 1000 |
| Scratch resistance | DIN 68861-4 ¹⁾ EN 438-2 | stress class [N] | 4B ≥ 2 | 4B ≥ 2 | 4B ≥ 2 |
| Calorific value | DIN 51900 | [MJ/kg] | ca. 16.5 | ca. 16.5 | - |
| Light fastness | ISO 4892 | [blue scale rating] | 6-7 | 6-7 | 6-7 |
| Surface resistance (antistatic behaviour) | EN 61340-2-3 (no static load) | [Ohm] | 10 ¹² | 10 ¹² | 10 ¹² |

¹⁾ Test standard for the assessment of surfaces. Testing was done following this. Further properties are included in the product data sheet.

Test Certificates and Approvals

| Product | Thickness [mm] | Classification | Test method |
|--|----------------------------------|---|--|
| Building industry RESOPAL® F RESOPLAN® F X-LINE B1 RESOPAL® F | 0.8-40 6-12 6-12 0.8-12 | B1 / B/C-s2, do B1 / B-s2, do B1 / B-s2, do M1 | DIN 4102-1 / EN 13823 DIN 4102-1 / EN 13823 DIN 4102-1 / EN 13823 NFP 92501 |
| Ship building RESOPAL® RESOPAL® F | 0.6-0.8 0.8-1.2 | low flame spread FTPC, appendix 1, part 2 and 5 MED 96/98/EC | IMO Res. MSC.61(67) |
| Transportation (railway vehicles) RESOPAL® F | 0.8-20 | S4 / SR2 / ST2 | DIN 5510-2 7 DIN 54837 |
| Others RESOPAL® | | no affects in the contact with food | guideline 80.30, 1-3 (EG) + EN 1186 + ENV 13130 |

Other test certificates on request.

ORIGINAL RESOPAL® – Processing

An extract from the most important processing guidelines for RESOPAL®, RESOPAL® on substrate, RESOPAL® Massiv, RESOPLAN® and WILSONART® Solid Surface:

For professional processing of our products we recommend that you use our detailed processing documentation.

Storage

- In closed storage rooms, protected against moisture
- Under normal climatic conditions (20 °C, 40 - 70% relative humidity)
- Fully supported and lying flat (horizontally) on pallets, flat bases, etc.
- The topmost board of a stack covered completely

Drilling

- Drills should be suitable for plastics:
Twist drills with tip angle of 60 - 80 °
- Cutting speed for HSS drills approx. 0.8 m/s, for hard metal drills (HM) up to approx. 1.6 m/s
- Drilling hole diameter at least 10% greater than the screw shank for through screws
- Do not use countersunk head screws!

Use only HM, no auger or gimlet bits for WILSONART® Solid Surface!

Milling

- Spindle moulding machines with hard metal equipped cutters
- Cutting tool diameter approx. 100 mm
- Speed 3000 - 6000 rpm, for RESOPAL® 10000 rpm
- Cutting speed 15 - 30 m/s, for RESOPAL® approx. 60 m/s for spindle moulding machines and approx. 15 m/s for surface milling benches
- Form inside corners allways with a radius of 7 - 13 mm, to avoid notch cracks

- Surface milling benches can also be used, for WILSONART® Solid Surface cutting tools diameter approx. 15 - 60 mm, speed 8000 - 16000 rpm

Sawing

- With all woodworking machinery and hard metal equipped circular saw bench blades
- Optimum tooth pitch for circular saws 10 - 15 mm, for WILSONART® Solid Surface diameter approx. 300 mm / Z=72 - 96
- Speed 3000 - 4000 rpm
- Cutting speed 40 - 100 m/s, for RESOPAL® on substrate 40 - 60 m/s
- Feed speed 10 m/s, for RESOPAL® 10 - 30 m/s
- As from 3 mm board thickness also with portable circular saws from the back of the board

Compass saws can be used only conditionally, absolutely unsuitabel for WILSONART® Solid Surface.

Glueing RESOPAL® and WILSONART®-SSV

- With all commercially available glues and adhesives on stress-free substrates with flat surface such as chipboards, wood fiber boards or veneer boards; for WILSONART® Solid Surface adhesive WA 3001 and edge adhesive WA 8215 (SK 200)
- Pressing temperature for RESOPAL® depends in each case on data from the adhesive manufactura (unheated pressing / cold gluing and heated presses at room temperature maximum up to 70 °C)
- Make sure the the backing laminate is symmetrical!
For WILSONART® Solid Surface with a nonsymmetrical backing (SSV chipboard backing laminate) use only substrates 22 mm or thicker!

You will find detailed data in our processing documentation. Please request if required under +49 6078 80 405!

Original RESOPAL®

ORIGINAL RESOPAL® – The tender

Available application forms



Seminars

Advising better, selling more successfully



Our current seminars

The better you can advise, the more successfully you can sell. Comprehensive expertise in product and application questions is the prerequisite for being able to offer the customer optimum solutions. Our product training courses afford you decisive

advantages not only to meet the daily competition but to even more successful. Our practice-related seminars are held several times each year and if you wish, also in your premises.

RESOPAL® – The system

Collections and periods of validity



RESOPAL® – The work tools



INDEX – alphabetical

| Name | No. | Pg. | Pos. | Pg.+ | PG |
|--------------------|------|----------|------|------|--------|
| Absinth | • | 0631-60 | 21 | B23 | 02 |
| Affinity | •• | 0147-60 | 19 | B5 | 02 |
| Alabaster | | D 431-60 | 20 | A8 | 02 |
| Amarena Cherry | • | 4128-WH | 27 | C3 | 31 02 |
| Amazon | | D 478-60 | 19 | D6 | 02 |
| Amber Industry | •• | 1815-EM | 76 | B1 | 92 02 |
| Antilop | | 0565-60 | 19 | C5 | 02 |
| Aqua | | 0724-60 | 21 | A17 | 02 |
| Ara | • | 0763-60 | 21 | A16 | 02 |
| Arctic White | | 0179-60 | 19 | A2 | 02 |
| Arum | | 0641-60 | 21 | C22 | 02 |
| Asparagus | • | 0400-60 | 21 | A23 | 02 |
| Aubergine | | 0798-60 | 20 | E14 | 02 |
| Avian Cherry Quer | • | 4463-FW | 63 | D | 62 02 |
| Azul | | 0168-60 | 19 | C1 | 02 |
| Azur | | 0744-60 | 21 | B16 | 02 |
| Bali Blue | | D 472-60 | 20 | C15 | 02 |
| Baltic Sea | | D 475-60 | 21 | D18 | 02 |
| Beachshell | | D 392-60 | 20 | A11 | 02 |
| Beaver | | 0520-60 | 19 | E5 | 02 |
| Bergamot | • •• | 0617-60 | 21 | C24 | 02 |
| Black | • •• | 0901-60 | 19 | E3 | 02 |
| Black Ice | | 3472-20 | 103 | A3 | 105 02 |
| Black Ice | | 3472-HW | 117 | C3 | 02 |
| Bluebell | | D 361-60 | 20 | B15 | 02 |
| Bluebonnet | • | D 416-60 | 21 | D16 | 02 |
| Blue Ice | | D 319-60 | 21 | B18 | 02 |
| Boston Cherry Quer | • | 4403-FW | 63 | C | 65 02 |
| Brick | | 0310-60 | 20 | E11 | 02 |
| Brushed Alu | | 3900-GB | 121 | A2 | 122 |
| Brushed Brass | | 3901-GB | 121 | D1 | |
| Brushed Copper | | 3902-GB | 121 | C1 | |
| Brushed Titanium | | 3903-AN | 121 | B1 | 120 |
| Butternut | | 0323-60 | 20 | B11 | 02 |
| Button | | 0600-60 | 21 | D22 | 02 |
| Canary | | D 302-60 | 20 | C8 | 02 |
| Candy | •• | 0355-60 | 20 | C13 | 02 |
| Carambola | • •• | 0639-60 | 21 | D24 | 02 |
| Cashmere | | D 432-60 | 20 | A22 | 02 |
| Ceylon | • | 0424-60 | 20 | D9 | 02 |
| Chamomille | • | 0404-60 | 20 | C7 | 02 |
| Chocolate | • | 0547-60 | 19 | E6 | 02 |
| Chrome Gloss | | 3900-HG | 121 | A1 | |
| Cinnamon | | 0512-60 | 19 | D5 | 02 |
| Citynight | • •• | 4122-60 | 47 | D2 | 54 02 |
| Citynight | • •• | 4122-HW | 117 | A2 | 116 02 |
| Citynight | • •• | 4122-WS | 69 | C2 | 73 02 |
| Classy Elm | • | 4121-WH | 47 | A1 | 48 02 |
| Clay Fragment | | 3484-60 | 76 | C2 | 99 02 |
| Clay Fragment | | 3484-KS | 111 | B1 | 114 02 |
| Clear Teal | | D 378-60 | 21 | C19 | 02 |
| Clemantine | | 0336-60 | 20 | D10 | 02 |
| Cloud | • | D 391-60 | 21 | A18 | 02 |
| Cloudy Cement | •• | 3447-EM | 76 | A1 | 90 02 |
| Cloudy Cement | •• | 3447-KS | 111 | A2 | 112 02 |
| Cobalt | • | 0760-60 | 21 | E16 | 02 |
| Corat | | 9501-60 | 20 | C11 | 02 |
| Core Maple | • | 4438-EM | 35 | A2 | 37 02 |
| Corn | • | 0441-60 | 20 | B10 | 02 |
| Corten | | 4944-60 | 76 | D2 | 94 02 |
| Corten | | 4944-KS | 111 | B2 | 144 02 |
| Cottage Pine | • | 4123-WH | 47 | E1 | 46 02 |
| Cross Lined Alu | | 3908-SN | 121 | C3 | |
| Cross Ribbed Alu | | 3900-SQ | 121 | C2 | 123 |
| Crystal White | • | 1570-60 | 20 | A15 | 02 |
| Curry | | 0437-60 | 20 | C10 | 02 |
| Dawn | • | 0140-60 | 19 | B4 | 02 |
| Dazzling White | • | 9402-60 | 19 | B1 | 02 |
| Delft | • | D 473-60 | 20 | D15 | 02 |
| Delicious | | 0634-60 | 21 | C23 | 02 |
| Delicious Oak | • | 4116-WH | 35 | D3 | 34 02 |
| Delight Cherry | • | 4428-60 | 27 | D1 | 02 |
| Designer White | • | D 354-60 | 19 | A4 | 02 |
| Diego Oak | • •• | 4167-WH | 57 | C | 60 02 |
| Dove Grey | • •• | D 92-60 | 19 | C2 | 02 |
| Dresden Blue | • •• | D 346-60 | 21 | C16 | 02 |
| Driftwood | | 4136-WH | 75 | B1 | 82 02 |
| Dubai Ebony | • | 4485-WH | 35 | C3 | 44 02 |
| Ebony | • •• | 10622-60 | 19 | E2 | 02 |
| Emerald | | D 365-60 | 21 | D21 | 02 |
| Empire Slate | | 4943-EM | 76 | A2 | 96 02 |
| Empire Slate | | 4943-KS | 111 | A3 | 110 02 |
| Eternal Cherry | • | 4325-EM | 27 | C2 | 30 02 |
| Eternal Cherry | • | 4325-WS | 69 | A3 | 72 02 |
| Eternal Iron | | 3236-60 | 76 | B3 | 97 02 |
| Eternal Iron | | 3236-KS | 111 | B3 | 113 02 |
| Fiesta Reef | | D 451-60 | 20 | D13 | 02 |
| Finery | •• | 3207-EM | 76 | C1 | 98 02 |
| Finery | •• | 3207-KS | 111 | A1 | 112 02 |
| Finn Oak | • | 4414-60 | 47 | A3 | 02 |
| Flamingo | | 0328-60 | 20 | A13 | 02 |
| Frantic | •• | 4137-WH | 75 | B3 | 83 02 |

| Name | No. | Pg. | Pos. | Pg.+ | PG |
|---------------------|------|----------|------|------|--------|
| Fresco Blue | •• | 4942-EM | 76 | B2 | 93 02 |
| Garonne Oak | • | 4111-WH | 35 | A3 | 40 02 |
| Global Beech | • | 4306-60 | 27 | C1 | 02 |
| Gold | • | 0446-60 | 20 | C9 | 02 |
| Gooseberry | | 0638-60 | 21 | B24 | 02 |
| Gotland Cherry Quer | • | 4402-60 | 63 | A | 64 02 |
| Granic Vein | | 3540-90 | 103 | B | 106 02 |
| Grey Ice | | 3470-20 | 103 | A2 | 105 02 |
| Guadina Oak Quer | • | 4461-FW | 63 | B | 66 02 |
| Hickory | • | 4106-EM | 35 | A1 | 36 02 |
| Ice | • | 0727-60 | 21 | B17 | 02 |
| Indian Granite | | 3485-90 | 103 | B3 | 107 02 |
| Indian Granite | | 3485-HW | 117 | B1 | 02 |
| Infinity | • | 0300-60 | 20 | E12 | 02 |
| Ivory | • | 0112-60 | 20 | A7 | 02 |
| Jade | • | 0670-60 | 21 | B20 | 02 |
| Jardin | | 0630-60 | 21 | E22 | 02 |
| Jurassic Rock | | 3444-KS | 76 | C3 | 96 02 |
| Kentucky Saloon | •• | 4155-FW | 75 | C2 | 80 02 |
| Kiwi | • | 0640-60 | 21 | E24 | 02 |
| Lagoon | | D 419-60 | 21 | D19 | 02 |
| Leather | | 3118-90 | 75 | E2 | 89 02 |
| Lilac | •• | 0741-60 | 20 | C14 | 02 |
| Lime | | 0603-60 | 21 | A22 | 02 |
| Lined Alu | | 3908-LN | 121 | B3 | |
| Linen | | 3115-AJ | 75 | E1 | 88 02 |
| Lychee | | 0325-60 | 20 | B12 | 02 |
| Macassar | • | 4397-60 | 27 | E3 | 02 |
| Macassar | • | 4397-HW | 117 | A1 | 02 |
| Machiato Barque | | 4615-WH | 75 | D3 | 84 02 |
| Magas Oak | • | 4235-WH | 47 | B2 | 49 02 |
| Magas Oak | • | 4235-WS | 69 | B2 | 72 02 |
| Majestic | • | 0767-60 | 20 | E15 | 02 |
| Mandarin Red | • | 1511-60 | 20 | D12 | 02 |
| Maroon Ash | • | 4200-WH | 27 | E1 | 02 |
| Maroua Zebrano | • | 4125-WH | 47 | E3 | 55 02 |
| Matt Alu | | 3908-GN | 121 | A3 | |
| May Green | | 0625-60 | 20 | E7 | 02 |
| Miami | | 0636-60 | 21 | C21 | 02 |
| Midori | | D 421-60 | 21 | E21 | 02 |
| Milano Quer | • | 4408-FW | 63 | E | 67 02 |
| Mint | | 0667-60 | 21 | A21 | 02 |
| Mississippi Pine | •• | 4134-EM | 75 | A2 | 78 02 |
| Mono Deluxe | • | 4332-EM | 35 | D2 | 02 |
| Moon Rock | | 3488-HW | 117 | B2 | 02 |
| Moon Rock | | 3488-KS | 111 | C2 | 02 |
| Moon Rock | | 3488-XX | 103 | C2 | 108 02 |
| Moon Walk | | 3489-KS | 111 | C1 | 115 02 |
| Moon Walk | | 3489-XX | 103 | C1 | 108 02 |
| Moss | | 0665-60 | 21 | E23 | 02 |
| Mountain Lodge | • | 4335-WH | 47 | C3 | 51 02 |
| Navy | • | 9440-60 | 21 | E17 | 02 |
| Nevada Saloon | •• | 4156-FW | 75 | C1 | 02 |
| Nile Green | • | D 362-60 | 21 | C20 | 02 |
| Noce Australia | • | 4261-60 | 35 | E3 | 45 02 |
| Noce Lugo | • | 4260-60 | 47 | B3 | 02 |
| Noce Lugo | • | 4260-WS | 69 | B3 | 71 02 |
| Noce Lyon | • •• | 4232-EM | 35 | C2 | 42 02 |
| Noce Praliné | • •• | 4452-60 | 35 | E1 | 43 02 |
| Noce Romantica | • | 4447-EM | 27 | D3 | 32 02 |
| North Sea | • | D 90-60 | 19 | D2 | 02 |
| Novara Elm | • | 4118-WH | 35 | E2 | 39 02 |
| Opaline | | D 377-60 | 21 | A19 | 02 |
| Orchid | | 9456-60 | 20 | B14 | 02 |
| Ottawa Maple | • | 4209-EM | 27 | B3 | 02 |
| Pablo Oak | • •• | 4168-WH | 57 | D | 61 02 |
| Pacific | | 0743-60 | 21 | C17 | 02 |
| Paprika | | 0314-60 | 20 | E10 | 02 |
| Parrot | | 9429-60 | 21 | D23 | 02 |
| Path Finder | | 4945-60 | 76 | E3 | 97 02 |
| Path Finder | | 4945-HW | 117 | C2 | 119 02 |
| Patina Rock | | 4939-HW | 117 | B3 | 02 |
| Patina Rock | | 4939-KS | 111 | C3 | 02 |
| Patina Rock | | 4939-XX | 103 | C3 | 109 02 |
| Pearl White | • •• | 0105-60 | 19 | A6 | 02 |
| Peony | • | 0402-60 | 20 | B7 | 02 |
| Petrol | | 0602-60 | 21 | B19 | 02 |
| Pewter | • | D 73-60 | 19 | D1 | 02 |
| Piave Cherry | • •• | 4109-WH | 27 | D2 | 26 02 |
| Pinasta | •• | 4131-WH | 75 | A3 | 79 02 |
| Pistacio | | 0666-60 | 21 | B21 | 02 |
| Plane Marked Maple | • | 4105-FW | 27 | A3 | 29 02 |
| Platin Beech | • | 4301-60 | 35 | B1 | 02 |
| Plumbum | | 3478-EM | 76 | A3 | 91 02 |
| Polar White | | 0320-60 | 20 | A14 | 02 |
| Pongee | • | D 435-60 | 20 | A10 | 02 |
| Porcelain | | 9512-60 | 21 | A24 | 02 |
| Port | • | D 14-60 | 20 | E13 | 02 |
| Primerose | • •• | 0425-60 | 20 | D7 | 02 |
| Provence | •• | 0742-60 | 20 | D14 | 02 |
| Putty | | 1503-60 | 19 | B6 | 02 |
| Rain | •• | 0135-60 | 19 | B2 | 02 |

| Name | No. | Pg. | Pos. | Pg.+ | PG |
|------------------|------|----------|------|------|--------|
| Real Ash | • | 4360-WH | 27 | B2 | 02 |
| Real Ash | • | 4360-WS | 69 | A2 | 71 02 |
| Ribbed Alu | | 3900-LM | 121 | B2 | 122 |
| Ruby Limescale | | 3533-EM | 76 | E2 | 100 02 |
| Rustic Oak | • | 4344-EM | 35 | B3 | 41 02 |
| Rusty Steel | | 4940-HW | 117 | C1 | 02 |
| Rusty Steel | | 4940-KS | 76 | D3 | 95 02 |
| Rusty Tin | | 4941-KS | 76 | D1 | 74 02 |
| Sabulous Rock | | 4917-90 | 103 | B1 | 106 02 |
| Shadow | • •• | D 96-60 | 19 | D4 | 02 |
| Shogun | | D 414-60 | 21 | C18 | 02 |
| Siena | | 9451-60 | 20 | D11 | 02 |
| Silica | • | 0531-60 | 19 | C6 | 02 |
| Silver Grey | • •• | 0160-60 | 19 | C3 | 02 |
| Silver Oak | • | 4228-WH | 47 | C1 | 02 |
| Silver Pine | • | 4339-WH | 47 | C2 | 02 |
| Silver Pine | • | 4339-WS | 69 | C1 | 70 02 |
| Slate Grey | | D 91-60 | 19 | E4 | 02 |
| Snow White | • •• | 9417-60 | 19 | A5 | 02 |
| Soft Elm | • •• | 4470-FW | 47 | A2 | 02 |
| Soft Elm | • •• | 4470-WS | 69 | B1 | 70 02 |
| Soft Grey | •• | 15000-60 | 19 | C4 | 02 |
| Soiree | | 0781-60 | 21 | E18 | 02 |
| Solano Oak | • •• | 4165-WH | 57 | A | 58 02 |
| Spring | | 0626-60 | 21 | B22 | 02 |
| Storm | | 10542-60 | 19 | E1 | 02 |
| Sun Maple | • •• | 4367-EM | 27 | B1 | 02 |
| Sun Maple | • •• | 4367-WS | 69 | A1 | 70 02 |
| Sunflower | • •• | 0426-60 | 20 | E8 | 02 |
| Sunny | • | 0439-60 | 20 | B9 | 02 |
| Sylvan Planet | | 4174-WH | 75 | D1 | 86 02 |
| Sylvan Star | | 4175-WH | 75 | D2 | 87 02 |
| Tauern Larch | • •• | 4103-EM | 27 | A1 | 02 |
| Teal | | 9450-60 | 21 | E19 | 02 |
| Texas Saloon | •• | 4157-FW | 75 | C3 | 81 02 |
| Tibetan Jade | • | D 443-60 | 21 | E20 | 02 |
| Tideland | | 3480-60 | 76 | E1 | 101 02 |
| Tin | | 0150-60 | 19 | D3 | 02 |
| Toscana Elm | • | 4158-WH | 35 | D1 | 02 |
| Traffic White | • •• | 0104-60 | 19 | A1 | 02 |
| Tropic Reed | | 4399-WS | 75 | E3 | 84 02 |
| Transition | • | 0120-60 | 19 | B3 | 02 |
| Tyrol Green | • | D 351-60 | 21 | D20 | 02 |
| Ultramarine | | 9497-60 | 21 | D17 | 02 |
| Ultra White | | 6001-60 | 19 | A3 | 02 |
| Unique Elm | • | 4448-EM | 35 | B2 | 02 |
| Valley Oak | • •• | 4166-WH | 57 | B | 59 02 |
| Velluto Cherry | • | 4113-EM | 35 | C1 | 38 02 |
| Vintage Festival | | 4475-WH | 75 | B2 | 50 02 |
| Vintage Oak | • | 4289-FW | 47 | D1 | 85 02 |
| Viola Cherry | • | 4115-EM | 47 | B1 | 52 02 |
| Visby Maple | • •• | 4104-EM | 27 | A2 | 28 02 |
| Washy Elm | | 4129-WH | 75 | A1 | 77 02 |

INDEX – numerical

| No. | Name | Pg. | Pos. | Pg.+ | PG |
|----------|--------------------|-----|------|------|----|
| 0104-60 | • • Traffic White | 19 | A1 | | 02 |
| 0105-60 | • • Pearl White | 19 | A6 | | 02 |
| 0112-60 | • Ivory | 20 | A7 | | 02 |
| 0120-60 | • Transition | 19 | B3 | | 02 |
| 0135-60 | • • Rain | 19 | B2 | | 02 |
| 0140-60 | • Dawn | 19 | B4 | | 02 |
| 0147-60 | • • Affinity | 19 | B5 | | 02 |
| 0150-60 | • Tin | 19 | D3 | | 02 |
| 0160-60 | • • Silver Grey | 19 | C3 | | 02 |
| 0168-60 | • Azul | 19 | C1 | | 02 |
| 0179-60 | • Arctic White | 19 | A2 | | 02 |
| 0300-60 | • Infinity | 20 | E12 | | 02 |
| 0310-60 | • Brick | 20 | E11 | | 02 |
| 0314-60 | • Paprika | 20 | E10 | | 02 |
| 0320-60 | • Polar White | 20 | A14 | | 02 |
| 0323-60 | • Butternut | 20 | B11 | | 02 |
| 0324-60 | • Water Lily | 20 | B13 | | 02 |
| 0325-60 | • Lychee | 20 | B12 | | 02 |
| 0326-60 | • Water Melon | 20 | C12 | | 02 |
| 0328-60 | • • Flamingo | 20 | A13 | | 02 |
| 0336-60 | • Clementine | 20 | D10 | | 02 |
| 0340-60 | • • Zinnia | 20 | E9 | | 02 |
| 0355-60 | • • Candy | 20 | C13 | | 02 |
| 0400-60 | • Asparagus | 21 | A23 | | 02 |
| 0402-60 | • Peony | 20 | B7 | | 02 |
| 0404-60 | • Chamomille | 20 | C7 | | 02 |
| 0413-60 | • Zitrus | 20 | B8 | | 02 |
| 0424-60 | • Ceylon | 20 | D9 | | 02 |
| 0425-60 | • • Primrose | 20 | D7 | | 02 |
| 0426-60 | • • Sunflower | 20 | E8 | | 02 |
| 0437-60 | • Curry | 20 | C10 | | 02 |
| 0439-60 | • Sunny | 20 | B9 | | 02 |
| 0441-60 | • Corn | 20 | B10 | | 02 |
| 0446-60 | • Gold | 20 | C9 | | 02 |
| 0512-60 | • Cinnamon | 19 | D5 | | 02 |
| 0520-60 | • Beaver | 19 | E5 | | 02 |
| 0531-60 | • Silica | 19 | C6 | | 02 |
| 0547-60 | • Chocolate | 19 | E6 | | 02 |
| 0565-60 | • Antilop | 19 | C5 | | 02 |
| 0600-60 | • Button | 21 | D22 | | 02 |
| 0602-60 | • Petrol | 21 | B19 | | 02 |
| 0603-60 | • Lime | 21 | A22 | | 02 |
| 0617-60 | • • Bergamot | 21 | C24 | | 02 |
| 0625-60 | • May Green | 20 | E7 | | 02 |
| 0626-60 | • Spring | 21 | B22 | | 02 |
| 0630-60 | • Jardin | 21 | E22 | | 02 |
| 0631-60 | • Absinth | 21 | B23 | | 02 |
| 0634-60 | • Delicious | 21 | C23 | | 02 |
| 0636-60 | • Miami | 21 | C21 | | 02 |
| 0638-60 | • Gooseberry | 21 | B24 | | 02 |
| 0639-60 | • • Carambola | 21 | D24 | | 02 |
| 0640-60 | • Kiwi | 21 | E24 | | 02 |
| 0641-60 | • Arum | 21 | C22 | | 02 |
| 0665-60 | • Moss | 21 | E23 | | 02 |
| 0666-60 | • Pistacio | 21 | B21 | | 02 |
| 0667-60 | • Mint | 21 | A21 | | 02 |
| 0670-60 | • Jade | 21 | B20 | | 02 |
| 0724-60 | • Aqua | 21 | A17 | | 02 |
| 0727-60 | • Ice | 21 | B17 | | 02 |
| 0741-60 | • • Lilac | 20 | C14 | | 02 |
| 0742-60 | • • Provence | 20 | D14 | | 02 |
| 0743-60 | • Pacific | 21 | C17 | | 02 |
| 0744-60 | • Azur | 21 | B16 | | 02 |
| 0760-60 | • Cobalt | 21 | E16 | | 02 |
| 0763-60 | • Ara | 21 | A16 | | 02 |
| 0767-60 | • Majestic | 20 | E15 | | 02 |
| 0781-60 | • Soiree | 21 | E18 | | 02 |
| 0798-60 | • Aubergine | 20 | E14 | | 02 |
| 0901-60 | • • Black | 19 | E3 | | 02 |
| 1503-60 | • Putty | 19 | B6 | | 02 |
| 1500N-60 | • • Soft Grey | 19 | C4 | | 02 |
| 1511-60 | • Mandarin Red | 20 | D12 | | 02 |
| 1570-60 | • Crystal White | 20 | A15 | | 02 |
| 1815-EM | • • Amber Industry | 76 | B1 | 92 | 02 |
| 3115-AJ | • Linen | 75 | E1 | 88 | 02 |
| 3118-90 | • Leather | 75 | E2 | 89 | 02 |
| 3207-EM | • • Finery | 76 | C1 | 98 | 02 |
| 3207-KS | • • Finery | 111 | A1 | 112 | 02 |
| 3236-60 | • Eternal Iron | 76 | B3 | 97 | 02 |
| 3236-KS | • Eternal Iron | 111 | B3 | 113 | 02 |
| 3444-KS | • Jurassic Rock | 76 | C3 | 96 | 02 |
| 3447-EM | • • Cloudy Cement | 76 | A1 | 90 | 02 |
| 3447-KS | • • Cloudy Cement | 111 | A2 | 112 | 02 |
| 3470-20 | • Grey Ice | 103 | A2 | 105 | 02 |
| 3471-20 | • White Ice | 103 | A1 | 104 | 02 |
| 3472-20 | • Black Ice | 103 | A3 | 105 | 02 |
| 3472-HW | • Black Ice | 117 | C3 | | 02 |
| 3478-EM | • Plumbum | 76 | A3 | 91 | 02 |
| 3480-60 | • Tideland | 76 | E1 | 101 | 02 |
| 3484-60 | • Clay Fragment | 76 | C2 | 99 | 02 |
| 3484-KS | • Clay Fragment | 111 | B1 | 114 | 02 |
| 3485-90 | • Indian Granite | 103 | B3 | 107 | 02 |

| No. | Name | Pg. | Pos. | Pg.+ | PG |
|---------|-------------------------|-----|------|------|----|
| 3485-HW | • Indian Granite | 117 | B1 | | 02 |
| 3488-HW | • Moon Rock | 117 | B2 | | 02 |
| 3488-KS | • Moon Rock | 111 | C2 | | 02 |
| 3488-XX | • Moon Rock | 103 | C2 | 108 | 02 |
| 3489-KS | • Moon Walk | 111 | C1 | 115 | 02 |
| 3489-XX | • Moon Walk | 103 | C1 | 108 | 02 |
| 3533-EM | • Ruby Limescale | 76 | E2 | 100 | 02 |
| 3540-90 | • Granic Vein | 103 | B2 | 106 | 02 |
| 3900-GB | • Brushed Alu | 121 | A2 | 122 | |
| 3900-HG | • Chrome Gloss | 121 | A1 | | |
| 3900-LM | • Ribbed Alu | 121 | B2 | 122 | |
| 3900-SQ | • Cross Ribbed Alu | 121 | C2 | 123 | |
| 3901-GB | • Brushed Brass | 121 | D1 | | |
| 3902-GB | • Brushed Copper | 121 | C1 | | |
| 3903-AN | • Brushed Titanium | 121 | B1 | 120 | |
| 3908-GN | • Matt Alu | 121 | A3 | | |
| 3908-LN | • Lined Alu | 121 | B3 | | |
| 3908-SN | • Cross Lined Alu | 121 | C3 | | |
| 4103-EM | • • Tauern Larch | 27 | A1 | | 02 |
| 4104-EM | • • Visby Maple | 27 | A2 | 28 | 02 |
| 4105-FW | • • Plane Marked Maple | 27 | A3 | 29 | 02 |
| 4106-EM | • Hickory | 35 | A1 | 36 | 02 |
| 4109-WH | • • Piave Cherry | 27 | D2 | 26 | 02 |
| 4110-WH | • Wenge Nakuru | 27 | E2 | 33 | 02 |
| 4111-WH | • Garonne Oak | 35 | A3 | 40 | 02 |
| 4113-EM | • Velluto Cherry | 35 | C1 | 38 | 02 |
| 4115-EM | • Viola Cherry | 47 | B1 | 52 | 02 |
| 4116-WH | • Delicious Oak | 35 | D3 | 34 | 02 |
| 4118-WH | • Novara Elm | 35 | E2 | 39 | 02 |
| 4121-WH | • Classy Elm | 47 | A1 | 48 | 02 |
| 4122-60 | • • Citynight | 47 | D2 | 54 | 02 |
| 4122-HW | • • Citynight | 117 | A2 | 116 | 02 |
| 4122-WS | • • Citynight | 69 | C2 | 73 | 02 |
| 4123-WH | • Cottage Pine | 47 | E1 | 46 | 02 |
| 4124-WH | • Wenge Opaque | 47 | E2 | 53 | 02 |
| 4125-WH | • Maroua Zebrano | 47 | E3 | 55 | 02 |
| 4128-WH | • Amarena Cherry | 27 | C3 | 31 | 02 |
| 4129-WH | • Washy Elm | 75 | A1 | 77 | 02 |
| 4131-WH | • • Pinasta | 75 | A3 | 79 | 02 |
| 4134-EM | • • Mississippi Pine | 75 | A2 | 78 | 02 |
| 4136-WH | • Driftwood | 75 | B1 | 82 | 02 |
| 4137-WH | • • Frantic | 75 | B3 | 83 | 02 |
| 4155-FW | • • Kentucky Saloon | 75 | C2 | 80 | 02 |
| 4156-FW | • • Nevada Saloon | 75 | C1 | | 02 |
| 4157-FW | • • Texas Saloon | 75 | C3 | 81 | 02 |
| 4158-WH | • Toscana Elm | 35 | D1 | | 02 |
| 4165-WH | • • Solano Oak | 57 | A | 58 | 02 |
| 4166-WH | • • Valley Oak | 57 | B | 59 | 02 |
| 4167-WH | • • Diego Oak | 57 | C | 60 | 02 |
| 4168-WH | • • Pablo Oak | 57 | D | 61 | 02 |
| 4174-WH | • Sylvan Planet | 75 | D1 | 86 | 02 |
| 4175-WH | • Sylvan Star | 75 | D2 | 87 | 02 |
| 4200-WH | • Maroon Ash | 27 | E1 | | 02 |
| 4209-EM | • Ottawa Maple | 27 | B3 | | 02 |
| 4228-WH | • Silver Oak | 47 | C1 | | 02 |
| 4232-EM | • • Noce Lyon | 35 | C2 | 42 | 02 |
| 4235-WH | • Magas Oak | 47 | B2 | 49 | 02 |
| 4235-WS | • Magas Oak | 69 | B2 | 72 | 02 |
| 4260-60 | • Noce Lugo | 47 | B3 | | 02 |
| 4260-WS | • Noce Lugo | 69 | B3 | 71 | 02 |
| 4261-60 | • Noce Australia | 35 | E3 | 45 | 02 |
| 4289-FW | • Vintage Oak | 47 | D1 | 50 | 02 |
| 4301-60 | • Platin Beech | 35 | B1 | | 02 |
| 4306-60 | • Global Beech | 27 | C1 | | 02 |
| 4325-EM | • Eternal Cherry | 27 | C2 | 30 | 02 |
| 4325-WS | • Eternal Cherry | 69 | A3 | 72 | 02 |
| 4332-EM | • Mono Deluxe | 35 | D2 | | 02 |
| 4335-WH | • Mountain Lodge | 47 | C3 | 51 | 02 |
| 4339-WH | • Silver Pine | 47 | C2 | | 02 |
| 4339-WS | • Silver Pine | 69 | C1 | 70 | 02 |
| 4344-EM | • Rustic Oak | 35 | B3 | 41 | 02 |
| 4360-WH | • Real Ash | 27 | B2 | | 02 |
| 4360-WS | • Real Ash | 69 | A2 | 71 | 02 |
| 4367-EM | • • Sun Maple | 27 | B1 | | 02 |
| 4367-WS | • • Sun Maple | 69 | A1 | 70 | 02 |
| 4397-60 | • Macassar | 27 | E3 | | 02 |
| 4397-HW | • Macassar | 117 | A1 | | 02 |
| 4399-WS | • Tropic Reed | 75 | E3 | 84 | 02 |
| 4402-60 | • • Gotland Cherry Quer | 63 | A | 64 | 02 |
| 4403-FW | • Boston Cherry Quer | 63 | C | 65 | 02 |
| 4408-FW | • Milano Quer | 63 | E | 67 | 02 |
| 4414-60 | • Finn Oak | 47 | A3 | | 02 |
| 4428-60 | • Delight Cherry | 27 | D1 | | 02 |
| 4438-EM | • Core Maple | 35 | A2 | 37 | 02 |
| 4447-EM | • Noce Romantica | 27 | D3 | 32 | 02 |
| 4448-EM | • Unique Elm | 35 | B2 | | 02 |
| 4452-60 | • • Noce Praliné | 35 | E1 | 43 | 02 |
| 4461-FW | • Guadina Oak Quer | 63 | B | 66 | 02 |
| 4463-FW | • Avian Cherry Quer | 63 | D | 62 | 02 |
| 4470-FW | • • Soft Elm | 47 | A2 | | 02 |
| 4470-WS | • • Soft Elm | 69 | B1 | 70 | 02 |
| 4475-WH | • Vintage Festival | 75 | B2 | 85 | 02 |

| No. | Name | Pg. | Pos. | Pg.+ | PG |
|----------|---------------------|-----|------|------|----|
| 4485-WH | • Dubai Ebony | 35 | C3 | | 02 |
| 4490-HW | • Zebrano Nightfall | 117 | A3 | 118 | 02 |
| 4490-WH | • Zebrano Nightfall | 47 | D3 | 55 | 02 |
| 4490-WS | • Zebrano Nightfall | 69 | C3 | | 02 |
| 4615-WH | • Machiato Barque | 75 | D3 | 84 | 02 |
| 4917-90 | • Sabulous Rock | 103 | B1 | 106 | 02 |
| 4939-HW | • Patina Rock | 117 | B3 | | 02 |
| 4939-KS | • Patina Rock | 111 | C3 | | 02 |
| 4939-XX | • Patina Rock | 103 | C3 | 109 | 02 |
| 4940-HW | • Rusty Steel | 117 | C1 | | 02 |
| 4940-KS | • Rusty Steel | 76 | D3 | 95 | 02 |
| 4941-KS | • Rusty Tin | 76 | D1 | 74 | 02 |
| 4942-EM | • • Fresco Blue | 76 | B2 | 93 | 02 |
| 4943-EM | • Empire Slate | 76 | A2 | 96 | 02 |
| 4943-KS | • Empire Slate | 111 | A3 | 110 | 02 |
| 4944-60 | • Corten | 76 | D2 | 94 | 02 |
| 4944-KS | • Corten | 111 | B2 | 144 | 02 |
| 4945-60 | • Path Finder | 76 | E3 | 97 | 02 |
| 4945-HW | • Path Finder | 117 | C2 | 119 | 02 |
| 6001-60 | • Ultra White | 19 | A3 | | 02 |
| 9402-60 | • Dazzling White | 19 | B1 | | 02 |
| 9417-60 | • • • Snow White | 19 | A5 | | 02 |
| 9429-60 | • Parrot | 21 | D23 | | 02 |
| 9440-60 | • Navy | 21 | E17 | | 02 |
| 9450-60 | • Teal | 21 | E19 | | 02 |
| 9451-60 | • Siena | 20 | D11 | | 02 |
| 9456-60 | • Orchid | 20 | B14 | | 02 |
| 9497-60 | • Ultramarine | 21 | D17 | | 02 |
| 9501-60 | • Coral | 20 | C11 | | 02 |
| 9512-60 | • Porcelain | 21 | A24 | | 02 |
| 10542-60 | • Storm | 19 | E1 | | 02 |
| 10622-60 | • • • Ebony | 19 | E2 | | 02 |
| D 14-60 | • Port | 20 | E13 | | 02 |
| D 73-60 | • Pewter | 19 | D1 | | 02 |
| D 90-60 | • North Sea | 19 | D2 | | 02 |
| D 91-60 | • Slate Grey | 19 | E4 | | 02 |
| D 92-60 | • • • Dove Grey | 19 | C2 | | 02 |
| D 96-60 | • • • Shadow | 19 | D4 | | 02 |
| D 302-60 | • Canary | 20 | C8 | | 02 |
| D 319-60 | • Blue Ice | 21 | B18 | | 02 |
| D 346-60 | • • • Dresden Blue | 21 | C16 | | 02 |
| D 351-60 | • Tyrol Green | 21 | D20 | | 02 |
| D 354-60 | • Designer White | 19 | A4 | | 02 |
| D 361-60 | • Bluebell | 20 | B15 | | 02 |
| D 362-60 | • Nile Green | 21 | C20 | | 02 |
| D 365-60 | • Emerald | 21 | D21 | | 02 |
| D 377-60 | • Opaline | 21 | A19 | | 02 |
| D 378-60 | • Clear Teal | 21 | C19 | | 02 |
| D 391-60 | • Cloud | 21 | A18 | | 02 |
| D 392-60 | • Beachshell | 20 | A11 | | 02 |
| D 397-60 | • Waterfall | 21 | A20 | | 02 |
| D 403-60 | • White Sand | 20 | A9 | | 02 |
| D 414-60 | • Shogun | 21 | C18 | | 02 |
| D 416-60 | • Bluebonnet | 21 | D1 | | |

Key words

| | | | | | |
|------------------------------------|-----------|-------------------------------------|-----------|-------------------------------|-----------|
| Abrasion resistance | 16 | Facades | 182 - 189 | Made to order | 200 - 201 |
| | 169 - 177 | Facing with air space | 182 - 189 | Magnetic | 145 |
| Aluminium optic | 120 - 121 | Fantasy | 148 - 157 | Matt | 14 - 15 |
| Application forms | 207 | Feel | 14 - 17 | Matt gloss surfaces | 17 |
| Approvals | 205 | Fixing systems | 191 | Metal | 120 - 121 |
| | | Flooring | 169 - 177 | Metal optic | 120 - 121 |
| Baby bathtubs | 198 | Flush installation | 167 | Motiv in RESOPAL® | 149 - 157 |
| Balconies | 189 | Food area | 146 - 147 | | |
| Bathroom | 172 - 177 | Formats | 200 - 201 | NCS | 18 - 25 |
| Brand RESOPAL® | 04 | Furniture | 144 | | 124 - 125 |
| Brushed Metal | 120 - 121 | | 146 - 147 | | 129 |
| Brushed Wood | 68 - 73 | | 158 - 163 | | |
| | | | 179 - 181 | | |
| | | | | Operation rooms | 146 - 147 |
| Caravan | 142 | Gloss | 16 | | |
| Ceramic | 16 | | 116 - 117 | Patent | 04 |
| | 74 | | 169 - 171 | PEFC | 162 |
| | 76 | Glossary | 213 | Philosophy | 06 - 07 |
| | 95 - 96 | | | Plain Colours | 18 - 25 |
| | 110 - 115 | High abrasion resistance | 16 | | 124 - 125 |
| | 136 - 137 | | 169 - 171 | | 129 |
| Certificates | 205 | High gloss | 16 | Postforming | 165 |
| Characteristics of RESOPAL® | 138 - 139 | | 116 - 117 | | 200 - 201 |
| | 200 - 205 | History | 169 - 171 | Preface | 06 - 07 |
| Clinics | 146 - 147 | Horizontal | 04 | Processing | 206 |
| | 179 - 181 | Horizontal woods | 62 - 67 | Product data | 200 - 205 |
| Color in RESOPAL® | 181 | | 127 | Products | 132 - 198 |
| Colour fidelity | 213 | Hospitals | 62 - 67 | Pure White | 143 |
| Compacts | 179 - 181 | | 127 | | |
| Components | 159 - 162 | Hygienically active surface | 146 - 147 | Qualities | 200 - 205 |
| Construction of material | 138 - 139 | | 146 - 147 | | |
| Contents | 01 | Ideal collection | 165 | Real metal | 120 - 121 |
| Contzen'tration | 154 - 157 | Imprint | 213 | | 145 |
| Corporate philosophy | 06 - 09 | Index alphabetical | 208 | Reflection | 116 - 119 |
| Counters | 146 - 147 | Index numerical | 209 | | 120 - 121 |
| | | Individual design | 149 - 157 | | 169 - 171 |
| Digital in RESOPAL® | 149 - 157 | Indoor swimming pools | 146 - 147 | Renovation | 144 |
| Directly coated chipboard | 162 | | | RESOPAL® Direct | 144 |
| Doctors surgeries | 146 - 147 | Laboratories | 146 - 147 | RESOPAL® meets LED | 153 |
| | 179 - 181 | Large kitchens, restaurants, | | RESOPALIT® | 162 |
| Doors | 124 - 127 | butcher shops, bakeries | 146 - 147 | RESOPLAN® | 184 - 188 |
| | | LED | 153 | RESOPLEX® | 167 |
| Edges | 165 - 167 | Light weight | 160 - 161 | RE-Y-STONE® | 192 - 195 |
| | 200 - 201 | | 167 | Rights of illustration | 213 |
| Elements | 159 - 162 | | | | |
| Environment | 06 - 09 | | | | |
| | 192 - 195 | | | | |
| External application | 182 - 189 | | | | |

| | | | |
|-----------------------------|-----------|---------------------------------|-----------|
| Sample Service | 212 | Vectogramm | 181 |
| Sanitary facilities | 146 - 147 | Vehicles | 142 |
| | 172 - 177 | | 179 - 181 |
| Saunas | 146 - 147 | | |
| Scale of presentation | 213 | Wall protection | 162 |
| Screen printing in RESOPAL® | 149 - 151 | Warranty | 213 |
| Self-adhesive RESOPAL® | 144 | Washbasins | 198 |
| Seminars | 207 | Water proof | 172 - 177 |
| Service | 200 - 207 | Wet and damp areas | 146 - 147 |
| Shops applications | 140 - 141 | | 172 - 177 |
| Silver | 120 - 121 | | 179 - 181 |
| Slate structure | 16 | WILSONART® Solid Surface | 196 - 198 |
| | 103 | Wood structure | 14 - 15 |
| | 108 - 109 | | 68 - 73 |
| Smooth matt - EM | 15 | Wooden Spirit | 68 - 73 |
| Solid colour | | Woodgrains | 26 - 67 |
| throughout laminate | 143 | Woods | 26 - 75 |
| Solid surface | 196 - 198 | | 78 - 87 |
| Stock | 200 - 201 | | 116 - 118 |
| Stone structures | 16 | | 126 - 129 |
| | 102 - 109 | Work tools | 207 |
| | 110 - 115 | Worktops | 164 - 167 |
| Stones | 102 - 109 | | |
| | 110 - 115 | | |
| Stripe structure | 68 - 73 | | |
| Structures | 14 - 17 | | |
| | 138 - 139 | | |
| Substrates | 160 | | |
| Suitable for flooring | 16 | | |
| Surface protection | | | |
| for solid surface | 198 | | |
| Surfaces | 14 - 17 | | |
| | 138 - 139 | | |
| | 200 - 201 | | |
| Swimming pools | 146 - 147 | | |
| | | | |
| Technical data | 200 - 206 | | |
| Thicknesses | 200 - 201 | | |
| Three milimetre radius | 165 | | |
| Titanium High Wear | 169 - 170 | | |
| Toilets | 146 - 147 | | |
| | 172 - 177 | | |
| | 179 - 181 | | |
| Trainings | 207 | | |
| Trend collection | 207 | | |
| | | | |
| Upstands | 165 | | |

24 h-Sample-Service – Fax
+49 (0)6078 80 624



Muster-Service

Postfach 1120
64818 Groß-Umstadt | DEUTSCHLAND
info@resopal.de

Wir bitten um Übersendung folgender Muster:

Please send the following samples:

Nous demandons l'envoi des échantillons suivants:

Kommission | Commission

Design-Nr. | Design No. | No. du Dessin

Anzahl | Quantity | Quantité

Für weitere Informationen
bitten wir um Rücksprache

Please contact us
for further information

Veillez nous contacter
pour tout renseignement complémentaire

Adresse | Address

Firma | Company | Maison

Telefax | Fax | Télécopie

Telefon | Phone | Téléphone

c/o

Straße | Street | Rue

Ort | Place | Lieu

Datum | Date

Unterschrift | Signature

PRODUCT INFORMATION

WARRANTY

The contents of this book were compiled and checked according to the best of our knowledge and belief. However, no warranty for its correctness can be accepted. Liability of the publisher, the Resopal GmbH, and the editorial staff for personal injury and material or asset damage that nevertheless results from its use is excluded.

The partner companies are responsible for the contents of their pages. Liability on their part is also excluded.

COLOUR FIDELITY

The greatest care has been applied to the faithful rendition of the colours and decors displayed in this book. The Plain Colours collection have been printed separately in 7-colour printing. However, there can be slight deviations in colour for printing reasons.

ORIGINAL RESOPAL® colours and printed colours, which have an identical type of light, appear different however in another, such as when changing from daylight to incandescent light, because they have different spectral properties.

We therefore recommend that if a binding colour sample is required, the final choice of decor is made according to the ORIGINAL RESOPAL® laminate sample.

SCALE OF PRESENTATION

The full-page decors as well as the Metal on RESOPAL® and WILSONART® Solid Surface collections are illustrated 1:1; on all other overview pages, the decors are reduced by 50%.

- pp. Reference to page with large images with identical surface
- pp. D. Reference to page with large images with different surface

RIGHTS TO ILLUSTRATION

- p. 01 © Jan Freudiger
- p. 02/03 (various) | p. 10-13 | p. 18 | p. 26 | p. 34 | p. 46 | p. 56 | p. 62 | p. 68 | p. 74 | p. 102 | p. 110 | p. 116 | p. 120 | p. 144, left | p. 145, left | p. 154-157 | p. 159 | p. 166 | p. 169 | p. 176, at the bottom | p. 180 | p. 195, at the bottom
© contzentrade® photostudio
- p. 02/03 (various) | p. 05 | p. 165 | p. 167 at the bottom | p. 178 | p. 198
© Christoph Hess Fotodesign
- p. 06/07 © peppi18 – Fotolia.com
- p. 08, left © line-of-sight – Fotolia.com
- p. 08, right © Inga Nielsen – Fotolia.com
- p. 09, left © by paul – Fotolia.com
- p. 09, right © fotoping – Fotolia.com
- p. 149 © contrastwerkstatt – Fotolia.com
- p. 164 © Image Source – Fotolia.com
- p. 172/173 © Tupungato – Fotolia.com
- p. 179 © PRILL Mediendesign – Fotolia.com
- p. 182/183 © baumuwe – Fotolia.com
- p. 192/193 © imago13 – Fotolia.com
- p. 196 © KonArt – Fotolia.com
- S. 153 © Joscha Wiener Photography

The illustrations appear with friendly approval of the legal owners. Where these could not be found, claims will be compensated for if necessary within the scope of the customary agreements.

IMPRINT

Publisher

Resopal GmbH, Groß-Umstadt
www.resopal.de

Layout and design

Resopal GmbH, Groß-Umstadt;
KR3ATIV – Werbeatelier Schösser GbR,
Groß-Umstadt

Overall concept

Nina Kehler, Resopal GmbH, Groß-Umstadt

Consultation

Gerd Ohlhauser, Darmstadt

Copy editor

Bianca Schmand-Hannemann
MSWW PR-Agentur
Redaktionsteam Wilfried Wadsack e. K.,
Bad Oeynhausen

Material scans

KruseMedien GmbH, Vreden

Printing

Hofmann Druck, Nürnberg

Cover decor

4941-KS Rusty Tin

© Resopal GmbH 04/2015
All rights reserved
10 €

Rights reserved for errors, changes and improvements!

GLOSSARY

| ENGLISH | GERMAN | FRENCH |
|---------|------------|------------|
| Ash | Esche | Frêne |
| Beech | Buche | Hêtre |
| Cherry | Kirschbaum | Cerise |
| Elm | Ulme | Orme |
| Larch | Lärche | Mélèze |
| Maple | Ahorn | Erable |
| Maroon | Kastanie | Marronnier |
| Oak | Eiche | Chêne |
| Pine | Kiefer | Pin |
| Walnut | Nussbaum | Noyer |
| Wenge | Wenge | Wenge |
| Zebrano | Zebrano | Zebrano |



Die Oberfläche.

Resopal GmbH

Hans-Böckler-Straße 4
64823 Groß-Umstadt | GERMANY

Phone +49 6078 80 0
Fax +49 6078 80 624
info@resopal.de

Further information

Phone +49 1805 RESOPAL
+49 1805 7376725
In Germany 0,14 €/min.
Mobile network max. 0,42 €/min.

The costs of calling from abroad are charged at the local foreign network charges for Germany.

European Sales Offices in:

Austria
Switzerland
France
Belgium
Netherlands
Scandinavia
Great Britain
Poland
Hungary | Eastern Europe

www.resopal.de